



Product Name

3,4-Epoxy cyclohexylmethyl 3,4-Epoxy cyclohexane Carboxylate (TTA21P)
CAS NO: 2386-87-0

Specifications

Brand Name	TTA21P
Appearance	Pale Yellow to Colorless Liquid
Assay	97% min
Weight per Epoxide	126~135
Viscosity	220~450 cP
Color(Pt-Co)	50 APHA max
Water	0.05% max
Total Chlorine	100 ppm max
Package	200kgs Drum or 1mt IBC Drum
Shelf Life	Two Year

Details

CAS NO: 2386-87-0

Molecular Formula: C₁₄H₂₀O₄

- ★ General-purpose cycloaliphatic diepoxide
- ★ Excellent weathering
- ★ High-heat-distortion temperature
- ★ Optical adhesives and photo curing products: such as potting of optoelectronic devices, CD manufacturing, low-viscosity UV-curing printing inks etc.
- ★ Outdoor electrical and electronic products in electrical casting and electronic encapsulation; especially for insulation encapsulation and adhesive bonding and electronic products for those which request high resistance to Cold & Thermal Shock.

海南 Hainan

地址:海南省海口市滨海大道105号百方大厦12C
Add: 12C, The Form Mansion, Binhai Avenue 105, Haikou,
Hainan, China
邮编 PC: 570125
电话 Tel: 86-898-68540310 传真 Fax: 86-898-68540119
邮箱 Email: sales@zxchem.com.cn

上海 Shanghai

地址:上海市徐汇区漕宝路509号新漕河泾大厦9层
Add: 9F, New Caohejing Building, No.509, Caobao Road,
Xuhui District, Shanghai, China
邮编 PC: 200233
电话 Tel: 86-21-54265599 传真 Fax: 86-21-64821580
邮箱 Email: sales@zxchem.com.cn



海南中信化工有限公司
HAINAN ZHONGXIN CHEMICAL CO., LTD.



- ★ Outdoor coating and solvent-free coating with better weather resistant than acrylic - polyurethane coating.
- ★ Active diluent: Good dilution effect without bubbles and exudate, high surface finish, No effect on the basic performance of curing material of epoxy resin, such as curing shrinkage, heat distortion temperature, impact strength and tensile strength.
- ★ Electrical and electronic products, civil construction, anti-corrosion coatings and other general application of bisphenol A epoxy resin. Widely used in casting, winding, encapsulation, coatings, adhesives and other fields.
- ★ Polyvinyl chloride polycarbonate stabilizer, oil (Lubricating oil, cylinder oil, transformer oil) additives, etc.

海南 Hainan

地址:海南省海口市滨海大道105号百方大厦12C
Add: 12C, The Form Mansion, Binhai Avenue 105, Haikou,
Hainan, China
邮编 PC: 570125
电话 Tel: 86-898-68540310 传真 Fax: 86-898-68540119
邮箱 Email: sales@zxchem.com.cn

上海 Shanghai

地址:上海市徐汇区漕宝路509号新漕河泾大厦9层
Add: 9F, New Caohejing Building, No.509, Caobao Road,
Xuhui District, Shanghai, China
邮编 PC: 200233
电话 Tel: 86-21-54265599 传真 Fax: 86-21-64821580
邮箱 Email: sales@zxchem.com.cn